

## Surface and anti-corrosion coating

# Aluminium Spray A-100



### Protects against rust and corrosion | abrasion-resistant

WEICON Aluminium Spray A-100 is abrasion-proof, resistant to many diluted acids and lyes, as well as to atmospheric influences. It contains aluminium pigments with a purity grade of approx. 99.5%. It offers high-quality corrosion protection for all metal surfaces. It can be used in cooling and ventilation technology, combustion systems, pipelines and machine housings, fibre glass car body components, in model building, arts and crafts, toy manufacturing, and in many other applications.

#### Technische Daten

Application area	indoor and outdoor use	
Binder	Acrylate resin	
Pigment	Aluminium pigments	
Pigment purity	approx. 99.5% Al	
Metal content in dry film	~43 %	
Processing temperature	+5 to +35°C, ideally +18 to +35°C	
Recommended primer	Zinc Spray	
Consumption	120 ml/m <sup>2</sup>	
Layer thickness with 1.5 crosswise applications approx.	25 -35 µm	
dust-dry	10 min.	
cured after	4 h	
Cross cutting	DIN 53151/ISO 2409	Cross cutting test value 0 to 1
Cylindrical mandrel bend test	DIN EN ISO 1519	no hairline cracking
Topcoat	not required	
Density	0,9 g/cm <sup>3</sup>	
Temperature resistance	-50°C to +800°C	
ISSA Code	53.402.42	
Shelf life	24 mon.	

### Surface pre-treatment

Clean and degrease surfaces with WEICON Surface Cleaner.

### Processing

Shake can before use, until rattle of mixing pea is clearly audible. Apply evenly at room temperature (approx. +20 °C) from a distance of approx. 25 cm in crosswise layers. Dust-dry after 10 min., fully cured after approx. 4-6 hours.

### Storage

Pressurized container. Protect from direct sunlight and temperatures above +50°C.

### Safety and health

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Available sizes:

11050400 Aluminium Spray A-100, 400 ml

To the product detail page:



#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 [info@weicon.ae](mailto:info@weicon.ae)

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 [info@weicon.cz](mailto:info@weicon.cz)

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 [info@weicon.de](mailto:info@weicon.de)

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 [office@weicon.com](mailto:office@weicon.com)

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 [info@weicon.com.sg](mailto:info@weicon.com.sg)

WEICON Inc. Canada phone +1 877 620 8889 [info@weicon.ca](mailto:info@weicon.ca)

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 [info@weicon.es](mailto:info@weicon.es)

WEICON Italia S.r.l. Italy phone +39 (0) 010 2924 871 [info@weicon.it](mailto:info@weicon.it)

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 [info@weicon.co.za](mailto:info@weicon.co.za)

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 [info@weicon.com.tr](mailto:info@weicon.com.tr)