

# Zinc Spray



**Long-lasting cathodic corrosion protection | paintable |  
>1050 hours salt spray test according to DIN EN ISO 9227 |  
NSF registration**

WEICON Zinc Spray is approved by the German TÜV and provides all metal surfaces with a long-lasting cathodic corrosion protection. It forms a fast-drying, adherent protective layer of microfine zinc flakes. Even after more than 1050 hours in the salt spray test according to DIN EN ISO 9227, metal parts coated with WEICON Zinc Spray did not show any signs of corrosion. The zinc flakes form a resistant protective layer even against extreme weather and environmental conditions. That way, WEICON Zinc Spray fulfils higher requirements than those defined by the DIN EN ISO 1461 standard. WEICON Zinc Spray can be used as a high-grade anti-rust primer, for the coating of welded joints and drill holes, as a conductive intermediate layer for spot welding and wherever metal must be protected against corrosion.

## Surface and anti-corrosion coating

### Technische Daten

Application area	indoor and outdoor use	
Binder	Styrene alkyd	
Pigment	flaky zinc and aluminium pigments	
Pigment purity	ca. 99.9% Zn / ca. 99.9% Al	
Metal content in dry film	~70 %	
Processing temperature	+5 to +35°C, ideally +18 to +35°C °C	
Recommended primer	not required	
Consumption	30 ml/m²	
dust-dry	15 min.	
cured after	12 h	
Cross cutting	DIN 53151/ISO 2409	Cross cutting test value 0
Complies with	Registered in the NSF White Book	
Salt spray test	DIN 50021/DIN 53167	> 1.050 h
Cylindrical mandrel bend test	DIN EN ISO 1519	no hairline cracking
Topcoat	not required	
Density	1,1 g/cm³	
Temperature resistance	-50 to +500	
ISSA Code	53.402.06	
Shelf life	24 mon.	

### Surface pre-treatment

Clean and degrease surfaces with WEICON Surface Cleaner.

### Processing

Shake can before use until the mixing ball can be heard clearly. Spray on evenly and crosswise at room temperature (approx. 20°C) and at about 25 cm distance from the surface. Dust-dry after approx. 15 minutes, fully hardened after approx. 10-12 hours.

### Storage

Pressurized container. Protect from direct sunlight and temperatures above +50°C.

### Safety and health

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Available sizes:

11000400 Zinc Spray, 400 ml

#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 [info@weicon.ae](mailto:info@weicon.ae)

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 [info@weicon.cz](mailto:info@weicon.cz)

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 [info@weicon.de](mailto:info@weicon.de)

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 [office@weicon.com](mailto:office@weicon.com)

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 [info@weicon.com.sg](mailto:info@weicon.com.sg)

WEICON Inc. Canada phone +1 877 620 8889 [info@weicon.ca](mailto:info@weicon.ca)

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 [info@weicon.es](mailto:info@weicon.es)

WEICON Italia S.r.l. Italy phone +39 (0) 010 2924 871 [info@weicon.it](mailto:info@weicon.it)

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 [info@weicon.co.za](mailto:info@weicon.co.za)

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 [info@weicon.com.tr](mailto:info@weicon.com.tr)