

Easy-Mix RK-7300 Structural Acrylic Adhesive



very good adhesion to plastics and EPDM | high-strength | viscoplastic | impact-resistant

WEICON Easy-Mix RK-7300 is a fast-curing, solvent-free structural and construction adhesive based on MMA (methyl methacrylate). It adheres perfectly to a variety of materials and has a high adhesive strength. It can be applied universally for static and dynamic loads. High-strength bondings are also possible in case of low surface energy plastics, such as PE or PP. Its high-viscosity characteristics also permit material pairings with different expansion coefficients, such as plastic / aluminium or steel. Special fillers (glass beads) ensure a consistent adhesive gap of 0.25 mm. Maximum gap-bridging: 1 mm.

Characteristics

Base	methyl methacrylate
Texture	pasty
Colour	translucent / hazy white

Processing

Processing procedure	Easy-Mix
Processing temperature	+10°C to +40°C
Curing temperature	mind. +18 °C
Mixing ratio by weight	1:1
Viscosity of the mixture	170.000-200.000 mPa·s
Density of the mixture	1,00 g/cm ³
Gap bridging up to max.	1 mm

Curing

Pot life	at 20 °C	8 min.
Handling strength	(35 % strength)	60 min.
Working strength after	(50 % strength)	480 min.
Final strength	(100 % strength)	24 h

Mechanical properties after curing

Lap shear strength material thicken. 1,5mm DIN EN 1465	
Steel 1.0338 sandblasted	5 N/mm ²
Stainless steel V2A sandblasted	4 N/mm ²
Aluminium sandblasted	5 N/mm ²
PVC-rigid roughened	11 N/mm ²
CFRP	7 N/mm ²
ABS	8 N/mm ²
PC (polycarbonate)	6 N/mm ²
GFRP	7 N/mm ²
PMMA	6 N/mm ²
Polyamide 6.6	3 N/mm ²
POM (polyoxymethylene)	5 N/mm ²
PE-HD	5 N/mm ²
PP (polypropylene)	6 N/mm ²
PTFE (polytetrafluorethylene)	2 N/mm ²
EPDM (Shore A70)	1 N/mm ²

Thermal parameters

Temperature resistance	-55°C to +100°C	
Tg after curing at room temperature (DSC)	51,5 °C	
Temperature conductivity	0,118 mm ² /s	
Thermal conductivity	DIN EN ISO 22007-4	0,15 W/m·K
Heat capacity	DIN EN ISO 22007-4	1,489 J/(g·K)

Electrical parameters

Resistance	DIN EN 62631-3-1	1,25 · 10 ¹³ Ω·m
------------	------------------	-----------------------------

Specific properties

ISSA Code	75.509.37
-----------	-----------

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Surface pre-treatment

Clean and dry bonding surfaces are essential for flawless adhesive bonding (e.g. cleaning and degreasing with WEICON Surface Cleaner). Smooth surfaces can be roughened mechanically.

Processing

WEICON Easy-Mix products can be processed straight from the double cartridge by means of the included static mixer. Dismiss the first 5 cm of the adhesive bead. The adhesive is applied to just one side. The specified pot life refers to a material batch of 10 ml at room temperature. Larger batch quantities will result in faster curing. Higher temperatures also reduce the pot life and curing time. (General rule: every increase by +10 °C above room temperature results in a decrease of the pot life and curing time by

half). Temperatures below +16 °C increase the pot life and curing time significantly. From approx. +5°C and below, no reaction takes place.

Note
Alle in diesem Technischen Datenblatt enthaltenen Angaben und Empfehlungen stellen keine zugesicherten Eigenschaften dar. Sie beruhen auf unseren Forschungsergebnissen und Erfahrungen. Sie sind jedoch unverbindlich, da wir für die Einhaltung der Verarbeitungsbedingungen nicht verantwortlich sein können, da uns die speziellen Anwendungsverhältnisse beim Verwender nicht bekannt sind. Eine Gewährleistung kann nur für die stets gleichbleibende hohe Qualität unserer Erzeugnisse übernommen werden. Wir empfehlen, durch ausreichende Eigenversuche festzustellen, ob von dem angegebenen Produkt die von Ihnen gewünschten Eigenschaften erbracht werden. Ein Anspruch daraus ist ausgeschlossen. Für falschen oder zweckfremden Einsatz trägt der Verarbeiter die alleinige Verantwortung.

Easy-Mix RK-7300 Structural Acrylic Adhesive

Storage

Shelf life of 6 months when unopened and stored in normal climate (+23°C and 50 % rel. air humidity).

Scope of delivery

Adhesive | Quadro Mixing Nozzle

Accessories

- 10650005 Quadro Mixing Nozzle, 1 PCE
- 10653050 Dispenser Easy-Mix D 50, 1 PCE
- 10850005 Glass Fibre Cloth Tape, 1 PCE, dark grey
- 12955175 Dosing Tip, 1 PCE

Conversion table

$(^{\circ}\text{C} \times 1,8) + 32 = ^{\circ}\text{F}$	$\text{Nm} \times 8,851 = \text{lb}\cdot\text{in}$
$\text{mm}/25,4 = \text{inch}$	$\text{Nm} \times 0,738 = \text{lb}\cdot\text{ft}$
$\mu\text{m}/25,4 = \text{mil}$	$\text{Nm} \times 141,62 = \text{oz}\cdot\text{in}$
$\text{N} \times 0,225 = \text{lb}$	$\text{mPa}\cdot\text{s} = \text{cP}$
$\text{N}/\text{mm}^2 \times 145 = \text{psi}$	$\text{N}/\text{cm} \times 0,571 = \text{lb}/\text{in}$
$\text{MPa} \times 145 = \text{psi}$	$\text{kV}/\text{mm} \times 25,4 = \text{V}/\text{mil}$

Available sizes:

- 10569050 Easy-Mix RK-7300 Structural Acrylic Adhesive, 50 g, translucent / hazy white

To the product detail page:



Note
 Alle in diesem Technischen Datenblatt enthaltenen Angaben und Empfehlungen stellen keine zugesicherten Eigenschaften dar. Sie beruhen auf unseren Forschungsergebnissen und Erfahrungen. Sie sind jedoch unverbindlich, da wir für die Einhaltung der Verarbeitungsbedingungen nicht verantwortlich sein können, da uns die speziellen Anwendungsverhältnisse beim Verwender nicht bekannt sind. Eine Gewährleistung kann nur für die stets gleichbleibende hohe Qualität unserer Erzeugnisse übernommen werden. Wir empfehlen, durch ausreichende Eigenversuche festzustellen, ob von dem angegebenen Produkt die von Ihnen gewünschten Eigenschaften erbracht werden. Ein Anspruch daraus ist ausgeschlossen. Für falschen oder zweckfremden Einsatz trägt der Verarbeiter die alleinige Verantwortung.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON Italia S.r.L. Italy phone +39 (0) 010 2924 871 info@weicon.it

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr