

Surface and anti-corrosion coating

Rust Protection 2000 PLUS



Particularly corrosion- and weather-resistant surface coating

WEICON Rust Protection 2000 PLUS is a particularly corrosion- and weather-resistant surface coating based on ferric oxide (hematite). By using highly-pure iron oxide pigments in a flaky arrangement, permanent weather-resistant and water-repellent surface protection is achieved. It can be used wherever metallic constructions or installations need long-term and visually appealing protection against extreme environmental and weather conditions. WEICON Rust Protection 2000 PLUS can be used on hall and steel structures, iron railing, lattice towers, fences, handrails, balcony grates, rolling gates, outdoor lights, and on all components vulnerable to corrosion.

Surface pre-treatment

Clean and degrease surfaces with WEICON Surface Cleaner.

Processing

Shake can well for two minutes before use, until the mixing pea is clearly audible. Keep shaking the can briefly every now and then during the application. Apply Rust Protection 2000 PLUS at room temperature (approx. +20 °C) from a distance of approx. 25 cm evenly in two crosswise layers.

Storage

Pressurized container. Protect from direct sunlight and temperatures above +50°C.

Safety and health

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes:

- 11012400 Rust Protection 2000 PLUS, 400 ml, anthracite
- 11013400 Rust Protection 2000 PLUS, 400 ml, grey

Technische Daten

Application area	indoor and outdoor use	
Binder	Alkyd resin	
Pigment	Lamellar haematite	
Pigment purity	> 90% iron oxide	
Metal content in dry film	~58 %	
Processing temperature	+5 to +35°C, ideally +18 to +35°C	
Recommended primer	not required	
Consumption	60 ml/m²	
Layer thickness with 1.5 crosswise applications approx.	60 - 80 µm	
dust-dry	30 min.	
cured after	24 h	
Cross cutting	DIN 53151/ISO 2409	Cross cutting test value 0 to 1
Cylindrical mandrel bend test	DIN EN ISO 1519	no hairline cracking
Topcoat	not required	
Density	1,3 g/cm³	
Temperature resistance	-50°C to +300°C	
ISSA Code	53.402.40/41	
Shelf life	24 mon.	

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON Italia S.r.l. Italy phone +39 (0) 010 2924 871 info@weicon.it

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr